



Haisun River table resin glue

Item	5301A-1	5301B-1	5301A-9	5301B-9
Appearance	Transparent liquid		Transparent liquid	
Viscosity(cps,25°C)	2500-3500	80-150	3500-4500	80-150
Specific gravity(g/cm ³ ,25°C)	1.2	0.8	1.2	0.8
Storage life(months)	6		6	
Proportion(Weight ratio)	A:B=3:1		A:B=3:1	
Application life(min,25°C × 100g)	60-90		60-90	
Gelation time(hr,25°C × 100g)	4-5		10-12	
Curing time(hr,25°C × 100g)	10-14		24	
Hardness(SHORE D _≥)	80		80	
Pouring thickness(cm/once)	3-5		8-10	
Packaging	20kg/ group (A-3barrel×5kg/barrel+B-1barrel×5kg/barrel)			

